

Tolerance on thickness according to DIN EN ISO 14632

Thickness	Min. Tolerance	Max. Tolerance	Tolerance
0.50	0.40	0.60	+/- 0.10
1.00	0.89	1.11	+/- 0.11
1.50	1.38	1.62	+/- 0.12
2.00	1.86	2.14	+/- 0.14
3.00	2.83	3.17	+/- 0.17
4.00	3.80	4.20	+/- 0.20
5.00	4.77	5.23	+/- 0.23
6.00	5.74	6.26	+/- 0.26
8.00	7.68	8.32	+/- 0.32
10.00	9.62	10.38	+/- 0.38
12.00	11.56	12.44	+/- 0.44
15.00	14.47	15.53	+/- 0.53
20.00	19.32	20.68	+/- 0.68
25.00	24.17	25.83	+/- 0.83
30.00	29.02	30.98	+/- 0.98
35.00	33.87	36.13	+/- 1.13
40.00	38.72	41.28	+/- 1.28
50.00	48.42	51.58	+/- 1.58